



Product Name : White in Moisture Cream

Code Number : 20161206A

Prescription :

	Ingredients	INCI	%
A	CV1005	Cyclomethicone	3.00
	KF-995	Cyclopentasiloxane	0.20
	Purolan IHD	Isohexadecane	2.00
	Salacos 816T	Cetyl Ethylhexanoate	2.00
	Cosmol 222	Diisostearyl Malate	0.75
	Cosmol 168ARV	Dipentaerythrityl Hexahydroxystearate/ Hexastearate/ Hexarosinate	1.00
	Salacos WO-6	Dipentaerythrityl/ Tri-Polyhydroxystearate	0.20
	Phenoxyethanol	Phenoxyethanol	0.20
	Adeka Not OG	Caprylyl Glycol	0.20
	Tocopherol 80	Tocopherol	0.05
B	1,3-BG	Butylene Glycol	4.00
	Glycerin	Glycerin	6.00
	Tornare	Glycosyl Trehalose/ Hydrogenated Starch Hydrolysate	3.00
	D-panthenol	Panthenol	0.50
	Niacinamide PC	Niacinamide	0.50
	Aquadew AN-100	Betaine	0.30
	Rheogic 260H	Sodium Polyacrylate	0.13
	Emalex SEG-07	Glyceryl Stearate/ PEG-10 Stearate	0.50
	Emalex GWIS-160N	PEG-60 Glyceryl Isostearate	0.60
	Cetyl Alcohol	Cetyl Alcohol	0.20
	Amisoft HS-11P	Sodium stearoyl glutamate	0.10
	WSK(2%)	Tremella Fuciformis Sporocarp Extract	2.00
	Water	Water	56.85
	Sensogel 200	Hydroxyethyl Acrylate/ Sodium Acrylyldimethyltaurate/ Steareth-20 Methacrylate Copolymer/ C13-C14 Isoparaffin/ Polysorbate 80/ Decyl Glucoside/ Glycerin	2.50
C	SF-9650	Dimethicone	3.00
	Belsil DM 350	Dimethicone	1.00

Prepare by Jack 2016/12/06

香林企業股份有限公司 KALIN ENTERPRISE CO.,LTD

總公司:11670台北市文山區景文街46之1號10樓
電話: + 886 289313301 傳真: + 886 289313323 統編:70840978

怡滙國際貿易(上海)有限公司 電話: + 86 21 54240077
香林企業股份有限公司(廣州辦事處) 電話: + 86 20 38889468



D	Dimethicone MICA2	Titanium Dioxide	6.00
	SI-T-CR-50-Z(80%)LHC	Methicone / Titanium Dioxide /Talc	1.00
E	perfume	Fragrance	0.02
	Phyto collage B(N)	Natto Gum	0.50
	Biocellact aloe vera B	Aloe Barbadosensis Leaf Extract	0.50
	Limuveil PD	Cladosiphon Novae-CaledoniaeExtract/ 1,2-Pentenediol/Phenoxyethanol/ Water	1.00
	Shiconix Liquid (BG)	Lithospermum Officinale Root Extract	0.20

Procedure :

- 1、Max and dissolve A phase at 80°C.
- 2、Max and dissolve B phase at 80°C.
- 3、Using a dispersion mill, add 【2】 to 【1】 and emulsify for 5 minutes at 2000rpm after homogenizer for 3 minutes at 3000rpm.
- 4、Cool to 60°C, add add C phase to 【3】 , with paddle mixing.
- 5、Cool to 40°C, add add D phase to 【4】 and dispersion with paddle mixing for 30 minutes after add E phase with paddle mixing.

※This formula is for reference only. If you need to commercialize, please confirm the test※

Prepare by Jack 2016/12/06

香林企業股份有限公司 KALIN ENTERPRISE CO.,LTD

總公司:11670台北市文山區景文街46之1號10樓
電話: + 886 289313301 傳真: + 886 289313323 統編:70840978

怡滙國際貿易(上海)有限公司 電話: + 86 21 54240077
香林企業股份有限公司(廣州辦事處) 電話: + 86 20 38889468