



Product name : Light Lip stain

No. : 20170627A

Features : Using **COSMOL 168ARV** increase shine on and using **ELDEW PS-203** for keeping moisturizing and **AMIHOPE LL** for modified skin feel .

Formulation :

	Ingredients	INCI Name	%
A.	NOMCORT HP-30VE	Hydrogenated Polydecene	12.00
	SALACOS 913	Isotridecyl Isononanoate	11.66
	COSMOL 43V	Polyglyceryl-2 Triisostearate	10.00
	SALACOS 5408	Pentaerythrityl Tetraethylhexanoate	24.94
	VERSAGEL M750	Mineral oil	10.00
	Polybutene 300H	Polybutene	20.00
	RHEOPEARL HC	Dextrin Palmitate	3.00
	JOJOBA OIL	SIMMONDSIA CHINENSIS (JOJOBA) SEED OIL	5.00
	ELDEW PS-203	Phytosteryl/ Octyldodecyl Lauroyl Glutamate	1.50
	COSMOL 168ARV	Dipentaerythrityl Hexahydroxystearate/ Hexastearate/ Hexarosinate	1.10
	TOCOPHEROL 80	Tocopherol	0.50
	ADEKA NOL OG	Caprylyl Glycol	0.30
B.	FD&C Red No.7	RED 7 LAKE	1.06
	FD&C Yellow No.5	YELLOW 5 LAKE	0.74
	SI-T-CR-50-Z (80%) LHC	Methicone / Titanium Dioxide / Talc	0.66
	AMIHOPE LL	Lauroyl Lysine	1.20
	Sericite Powder HM8325	Sericite	0.40
	SUNSPHERE H-122	Silica	0.50
	F-223	pigment	0.05

Process :

1. Mix phase A(Except Rheopearl HC) and heat to 70°C.
2. Cool down 【1】 , add Rheopearl HC to 【1】 and heat to 90°C.
3. Put 【2】 and phase B to Tri-Chilled Roller Mill grind twice.
4. Reheat 【3】 and vacuum defoaming.
5. Heat 【4】 to 70~80°C for filling mold.

※This formulation just for reference,if you would like commercialization, please confirm relevant testing.

Prepare by Emily 2017/6/27

香林企業股份有限公司 KALIN ENTERPRISE CO.,LTD

總公司:11670台北市文山區景文街46之1號10樓
電話: +886 289313301 傳真: +886 289313323 統編:70840978

怡滙國際貿易(上海)有限公司 電話: +86 21 54240077
香林企業股份有限公司(廣州辦事處) 電話: +86 20 38889468